


PRODUCT SUBMITTAL



WIRE-BOND[®]

Glass Block Reinforcing



MATERIAL CONFORMANCE

ASTM A82 / A82M - (Cold drawn steel wire)

Tensile Strength - 80,000 psi

Yield Point - 70,000 psi

ACI / ASCE 530 - (Building code requirements for masonry structures)

SHEET METAL - (Carbon Steel) **ASTM A1008 / A1008M**

Mill Galvanized / Zinc Coating: **ASTM A641 / A641M (0.10 Oz per sq ft)**

Hot Dip Galvanized after fabrication / Zinc Coating

ASTM A153 / A153M-B2 (1.50 oz per sq ft)

Stainless Steel **ASTM 580 / ASTM 580M Type 304** (Type 316 available on special order)

WIRE Recycled Content:

Mill Galvanized & Hot Dip,
82.8% Post-Consumer
17% Post Industrial / Pre -
Consumer

Stainless Steel,
97% Pre-Consumer
V O C Content - 0%

SIZES / FINISHES

GLASS BLOCK REINFORCING:

Manufactured to the same specifications as ladder type material except distance between longitudinal wire is 1-5/8" or 2". Continuous reinforcement ensures structurally sound glass block masonry

FINISH:

Hot Dip Galvanized



www.wirebond.com

MASONPRO, Inc.
43300 Seven Mile Road
Northville, MI 48167
1-800-659-4731
www.masonpro.com